

/ Ever since 1950, we've been developing innovative comprehensive solutions for arc welding and resistance spot-welding. Both of them weld processes that stand out for very high speed and deposition rates. Our Cold Metal Transfer process has swept away one old prejudice: that you can't weld aluminium and steel to one another. Day-in, day-out, we're working on our vision: to »decode the DNA of the arc«. No wonder that we're the welding-sector's technological leader worldwide, as well as being the European market leader.





# TO MANY PEOPLE, HIGH PERFORMANCE WELDING IS ONLY ABOUT SPEED. WE'VE ADDED SUPERIOR PRODUCTIVITY.

/ Wherever light-gauge sheets need to be welded together at high speed, welding systems from Fronius play an outstanding role. With wirefeed speeds of over 15 metres per minute and deposition rates of up to 8 kilograms per hour in single-wire processes, they meet all possible requirements regarding productivity and precision. What is more, Fronius tandem systems achieve wirefeed speeds of over 30 metres per minute, and deposition rates of up to 20 kilograms per hour. And when it comes to welding thick sheets and plates, Fronius welding systems really flex their muscles, catering to every possible wish regarding cost-effective performance.

#### **INNOVATIVE TECHNOLOGY**

/ Products from Fronius are characterised by their highperforming, rugged technology and stable wire guidance. Even at the highest speeds, these ensure 100 % reproducible, visually immaculate weld-seams.

## **SYSTEM SOLUTIONS**

/ If you're serious about exploiting the scope of excellent welding properties and functions to the full, you have to think in terms of systems. In conjunction with our peripherals, the digital power sources constitute thoroughly co-ordinated and extremely innovative high-performance welding systems that cater to every possible wish.

## **TECHNICAL KNOW-HOW AND MECHANICAL SKILL**

/ Perfect welding solutions result from the interplay of several factors: For a start, the welding systems themselves have to be top-class. As well as this, users need to have excellent technical know-how and mechanical skill. We make sure this is the case by giving welders thorough practical training on their new welding systems, on their own premises.

#### **HIGH PROCESS STABILITY**

/ Our welding systems have above-averagely long service lives. This is because their high-quality components are all superbly well made and designed for optimum interoperability. Much to the welder's benefit, thanks to the high process stability which is essential for achieving the desired speed and deposition rates.

## SERVICE THAT'S NEVER FAR FROM THE CUSTOMER

/ Just like our welding systems, our service staff are highperformers too, with capable teams of applications and service technicians delivering fast, expert 'on-the-spot' advice and support, 24 hours a day, 365 days a year.

## WE OFFER YOU WELDING SOLUTIONS THAT ARE ALWAYS A STEP AHEAD.

/ The utmost in product quality, economy and energy efficiency – that's what Fronius stands for. We have mastery of the entire welding spectrum and can guarantee a perfect interplay between all the components of our welding systems. See for yourself!


## TIME

/ A modified MAG process in which optimisation of the shielding gas and of the stick-out allows the deposition rate to be increased by up to 30 %. The power-source technology has been specifically tailored to the demands of the TIME Process.

## **CMT TWIN**

/ A simplified system configuration and synchronised start-up of two separately controllable power sources, two wire electrodes and a gas nozzle, combined with the tried-and-tested CMT process. Unbeatable arc stability coupled with deep penetration, optimum wetting to sidewalls, and low-spatter welding.













## **APPLICATION MODULE CMT TWIN**

#### MAX. WELDING SPEED IN PB POSITION

/ No undercutting

/ Reliable penetration

/ Virtually spatter-free

 $V_{wold} = 300 \text{ cm/min } (118.09 \text{ in/m})$ 

 $V_{wireL} = 15.5 \text{ m/min}$   $V_{wireT} = 6.2 \text{ m/min}$ 

(610.0 in/min) (236.14 in/min)

407 A 196 A

28.5 V 15.0 V



/ Steel, 3 mm (0.12 in)

## **BIGGEST 'a' DIMENSION IN PB POSITION**

/ No weldment manipulation needed / Ideal weld-seam position (at 45°)

/ Optimised wetting to sidewalls

 $V_{\text{model}} = 66 \text{ cm/min} (\sim 26 \text{ in/min})$ 

 $V_{wireL} = 15.0 \text{ m/min}$   $V_{wireT} = 8.0 \text{ m/min}$ 

(590.29 in/min) (314.84 in/min)

391 A 214 A

28.3 V 17.0 V



/ Steel, 10 mm (0.39 in), a = 6

## **EXTREMELY HIGH PROCESS STABILITY**

/ No need for any additional grinding off of

the primer coating

/ No weld-seam porosity

/ Virtually spatter-free

 $V_{weld} = 200 \text{ cm/min } (78.61 \text{ in/min})$ 

 $V_{wireI} = 14.5 \text{ m/min}$   $V_{wireT} = 7.5 \text{ m/min}$ 

(570.94 in/min) (295.49 in/min)

374 A 209 A

27.0 V 18.7 V



/ Primered steel, 8 mm (0.31 in), a = 3

#### PERFECT ROOT FORMATION

/ Homogeneous weld interface

/ Reliable sidewall fusion

/ No weld-pool backing needed

 $V_{weld} = 120 \text{ cm/min } (47.2 \text{ in/min})$ 

 $V_{wireL} = 7.1 \text{ m/min}$   $V_{wireT} = 7.5 \text{ m/min}$ 

(275.49 in/min) (295.49 in/min)

374 A 268 A

16.2 V 17.3 V



/ Steel, 8 mm (0.31 in)

## APPLICATION MODULE TIMETWIN

## **HIGHEST-QUALITY METALLURGICAL JOINS**

/ Tightly controlled thermal input / Low thermal load / Extremely low spattering  $V_{weld} = 180 \text{ cm/min (70.75 in/min)}$ 

 $V_{wireL} = 9.2 \text{ m/min}$   $V_{wireT} = 8.0 \text{ m/min}$  (354.19 in/min) (314.84 in/min)

230 A 200 A 21.4 V 20.4 V



/ CrNi, 2 mm (0.08 in)

## **HIGH SEAM QUALITY**

/ On many different thicknesses of metal / Reliable root fusion / Very low pore formation  $V_{model} = 200 \text{ cm/min } (78.61 \text{ in/min})$ 

 $V_{wireL} = 12.5 \text{ m/min}$   $V_{wireT} = 11.3 \text{ m/min}$  (492.24 in/m) (432.89 in/min)

235 A 213 A 21.1 V 20.3 V



/ Aluminium, 3 mm (0.12 in)

## **EXTREMELY HIGH DEPOSITION RATE**

/ Wirefeed speeds up to 30 m/min / Deposition rates up to 22 kg/h / Extremely stable arc achieved by fully digitised power-source know-how  $V_{weld} = 80 \text{ cm/min } (31.45 \text{ in/min})$ 

 $V_{wireL} = 15.5 \text{ m/min}$   $V_{wireT} = 15.0 \text{ m/min}$ 

(610.29 in/min) (590.29 in/min)

350 A 340 A 31.9 V 31.7 V



/ Steel, 8 mm (0.31 in)

#### **MULTI-PASS WELD**

/ Perfect welding properties in PF / Only small included angle needed / Higher productivity, as fewer passes are needed *Includes welding parameters from the root, filler and top passes* 

 $V_{weld} = 15 - 20 \text{ cm/min } (5.9 - 7.9 \text{ in/min})$ 

 $V_{wireL} = 8 - 10 \text{ m/min}$   $V_{wireT} = 5 - 8 \text{ m/min}$ 

(314.84 - 393.54 in/min) (196.79 - 314.84 in/min)

200 - 250 A 120 - 200 A

17.3 - 17.8 V 15.8 - 17.3 V



/ Aluminium, 40 mm (1.57 in), PF

## **APPLICATION MODULE TIME**

#### **ECONOMICAL**

/ Large 'a' dimension with small numbers of passes / Reliable penetration behaviour

/ Netiable penetration belia

/ Minimal distortion

Deposition rate 9.6 kg/h (21.16 lb/h)  $V_{weld} = 37 \ cm/min \ (14.6 \ in/min)$   $V_{wire} = 18 \ m/min \ (708.34 \ in/min)$   $360 \ A$ 



/ Steel, 15 mm (0.59 in), 3 passes, PF, a = 12

## **NARROW-GAP WELDING**

/ Good accessibility
/ Reliable sidewall fusion
/ Highly economical, thanks to
lower number of passes
compared to MAG


Beads 1 and 2: Beads 3/4/5/6:
Deposition rate Deposition rate

40 V

6.4-8.5 kg/h (14.1-18.7 lb/h) 11-12.3 kg/h (24.3-27.11 lb/h)

 $V_{weld} = 47/60 \ cm/min$   $V_{weld} = 30 - 46 \ cm/min$   $(18.5/23.6 \ in/min)$   $(11.8 - 18.11 \ in/min)$   $V_{wire} = 12/16 \ m/min$   $V_{wire} = 20 - 23 \ m/min$   $(472.24/629.64 \ in/min)$   $(787.04 - 905.09 \ in/min)$ 

210/310 A 390 - 420 A 34/37 V 42 - 46 V



/ Steel, 12 mm on 25 mm (0.47 in on 0.98)

## **POSITIONAL WELDING**

/ High weld-metal deposition, even in overhead position / Fine wetting to sidewalls

/ Reliable fusion of the root edge

Deposition rate 4.8 kg/h (10.58 lb/h)

 $V_{weld} = 40 \text{ cm/min (15.7 in/min)}$  $V_{wire} = 9.0 \text{ m/min (354.19 in/min)}$ 

250 A 31.5 V



/ Steel, 10 mm (0.39 in), a = 5

#### **EXTREMELY HIGH DEPOSITION RATE**

/ Perfect penetration cross-section

/ No undercutting

/ Distortion minimised by low thermal input


Deposition rate 16.2 kg/h (35.7 lb/h)

 $V_{wold} = 45 \text{ cm/min } (17.72 \text{ in/min})$ 

 $V_{wire} = 30 \text{ m/min (1180.54 in/min)}$ 

520 A

51 V




/ Steel, 20 mm (0.79 in), PA, a = 8

## **APPLICATION MODULE LASERHYBRID**

## 10 kW WELDING HEAD

/ New design for a focal length of 300 mm (11.8 in) and 10 kW of laser power





/ Steel, 12 mm (0.47 in)

#### **4 kW WELDING HEAD**

/ 10-year track record of successful deployment in the automobile industry.





/ Steel, 2.7 mm (0.1 in)

## 90° 4 kW WELDING HEAD

/ Angled design for optimum accessibility, e.g. in automotive axle production





/ Steel, 2 mm (0.08 in)

## 90° 8 kW WELDING HEAD

/ Ensures optimum accessibility in pipeline-construction projects





/ Steel, 12.3 mm (0.48 in)

## 10 kW WELDING HEAD

/ Optimum head-geometry for single-sided root fusion on steel sheets up to 10 mm (0.39 in) thick.





/ Steel, 16 mm (0.63 in)




## TIMETWIN

/ Is the name of a tandem process in which the weld process is synchronously controlled between two separately adjustable power sources. The two mutually insulated wire electrodes are routed through a single gas nozzle, thereby achieving perfect welding results.

TimeTwin welding process









## **LASERHYBRID**

/ This combination of laser and GMA welding makes it possible to exploit the advantages of each process to the full, and to create synergies. The high welding speed and concentrated energy of the laser can be combined with the GMA arc to achieve either of two possible benefits: maximum welding speed on light-gauge sheets, or maximum weld penetration depth on thicker materials.



## CMT TWIN: THE THRIFTIEST WAY TO WELD.

## **WIREFEED SPEED**

/ VR 1550 wirefeeder with 4-roller drive for smooth, precision feeding of the filler metal – regardless of where the wire is being fed from (bulk wire container or wire-spool).

## DIGITALLY CONTROLLED MIG/MAG WELDING POWER SOURCES

/ The two digitally controlled CMT welding power sources are perfectly attuned to one another by the unique system/process technology of CMT Twin. They come with a package of ideal characteristics covering every possible application.

## **COOLING UNIT**

/ The rugged and reliable FK 4000-R cooling unit is designed to dovetail with the modular concept of the welding system as a whole.



/ CMT Twin is based on the same set-up as the tried-and-tested TimeTwin process: two power sources, one torch and two mutually insulated contact tips ('Lead' and 'Trail'). To which have been added the outstanding welding properties of CMT. CMT Twin scores top marks for its high welding speeds and easy-to-use process control.



# LASERHYBRID: THE ADVANTAGES OF THE FULLY DIGITISED MIG PROCESS COMBINED WITH THE BENEFITS OF LASER WELDING.



## DIGITALLY CONTROLLED POWER SOURCE

/ LaserHybrid functions with a TPS 5000 welding power source. In order to fulfil the special requirements of LaserHybrid, the TPS 5000 comes equipped with a package of special characteristics.

/ Fronius LaserHybrid, the laser-MIG process from Fronius, unites the advantages of the industrial-scale MIG and laser-beam welding processes. And does so without taking on any of the disadvantages of either process. Fronius LaserHybrid marries the excellent gap-bridging ability and easy weld-seam preparation of MIG welding with the low thermal input, deep penetration and speed of the laser process. With Fronius LaserHybrid, it is possible to carry out automated joining of different aluminium and steel items at speeds of up to 8 metres per minute, in superlative quality.



## TIME: 30 % HIGHER DEPOSITION RATE THAN CONVENTIONAL MAG WELDING.

## TIME MANUAL WELDING TORCH

/ The 2-circuit cooling system ensures optimum cooling. Thanks to the continuously adjustable contact tip, this welding torch permits an extremely long stick-out (of between 15 and 25 mm). The longer stick-out means that the wire is heated up very strongly, allowing extremely high wirefeed speeds to be achieved, yet at a low amperage.



## DIGITALLY CONTROLLED MIG/MAG-WELDING POWER SOURCE

/ Higher performance also means that more power is required from the power source: The TIME 5000 Digital has an extremely long duty cycle, with possible working voltages of up to 48 V and a wirefeed speed of 30 m/min.

## **COOLING UNIT**

/ If you have more power, you need more cooling. The rugged and reliable FK 4000 cooling unit is designed to dovetail with the modular concept of the welding system as a whole.

/ The TIME Process is a technically more advanced version of the conventional MAG process. It has a long and successful track record in industry, for both manual and mechanical applications. The difference from conventional MAG welding is that the TIME Process has a longer wire stick-out on the welding torch, and a higher wirespeed. As a rule, it is possible to work with 2-component shielding gas. However, we recommend admixing helium for seams with an 'a' dimension above 8 mm, for metal thicknesses from 25 mm upwards, and for penetration cross-sections greater than 50 mm².



M,06,0049,EN v01 2012 aw16

# WE HAVE THREE DIVISIONS AND ONE PASSION: SHIFTING THE LIMITS.

/ What Günter Fronius started in 1945 in Pettenbach, Austria, has now become a modern day success story. Today, the company has around 3,000 employees worldwide and owns more than 850 active patents. Since the very beginning, our goal has not changed: to be the technology and quality leader. We shift the limits of what's possible. While others progress step by step, we innovate in leaps and bounds.

## **BATTERY CHARGING SYSTEMS**

/ We started a technological revolution with Active Inverter Technology and are now one of the leading suppliers in Europe. We are driven by the aim of providing intelligent energy management systems that ensure mobility stays as economically viable as possible in the twenty-first century.

## **WELDING TECHNOLOGY**

/ We develop welding technologies, such as entire systems for arc and resistance spot welding, and have set ourselves the task of making impossible weld joints possible. Our aim is to decode the "arc welding's DNA". We are the technology leader worldwide and the market leader in Europe.

## **SOLAR ELECTRONICS**

/ The greatest challenge of our time is to make the leap to a regenerative energy supply. Our vision is to use renewable energy to achieve energy independence. With our mainsconnected inverters and products for monitoring photovoltaic systems, we are now one of the leading suppliers in solar electronics.



Further information about all Fronius products and our global sales partners and representatives can be found at www.fronius.com

Fronius Canada Ltd.
2875 Argentia Road, Units 4,5 & 6
Mississauga, ON L5N 8G6
Canada
Telephone +1 905 288-2100
Fax +1 905 288-2101
sales.canada@fronius.com
www.fronius.ca

Fronius USA LLC 6796 Fronius Drive Portage, IN 46368 USA Telephone +1 877 FRONIUS sales.usa@fronius.com www.fronius-usa.com Fronius UK Limited
Maidstone Road, Kingston
Milton Keynes, MK10 0BD
United Kingdom
Telephone +44 1908 512 300
Fax +44 1908 512 329
sales.uk@fronius.com
www.fronius.co.uk

Fronius International GmbH Froniusplatz 1 4600 Wels Austria Telephone +43 7242 241-0 Fax +43 7242 241-953940 sales@fronius.com www.fronius.com